








Technical data

| | | |
|--|--|--|
| article: | <u>drapilux-155</u> | |
| texture: | atlas weave | |
| description: | check | |
| characteristics: |  flammstop | |
| |  drapilux akustik | |
| repeat (h/w): | approx. 92 cm (↕) x 140 cm (↔) | |
| material composition: | 100 % Polyester (<i>flame-retardant polyester Trevira CS</i>) | |
| width: | approx. 140 cm (↔) | |
| weight per sqm | approx. 225 g | |
| colours/designs | 5 designs <u>slight deviations in colour possible</u> | |
| official textile marks: | 100 % Polyester | |
| fire tests: | meeting international demand of DIN 4102 (B1), EN 13773 (Class 1), M1 Non Feu (B+F+E) , BS 5867 (GB), Classe 1 (I), IMO Res.MSC.307(88)-(2010 FTP Code) | |
| cleaning recommendation: |      | |
| rest shrinkage at 60°C: | approx. 1-2 % | |
| light resistance (ISO 105/B02): | grade 5-6 | (grades: 1 - 8) (8=excellent/ 1=insufficient) |
| washing resistance (ISO 105/C01): | grade 3-4 | (grades: 1 - 5) (5=excellent/ 1=insufficient) |
| rubbing test (ISO 105/X12) | dry/wet: grade 3-4 | (grades: 1 - 5) (5=excellent/ 1=insufficient) |
| <u>Martindale-test (DIN EN 14465):</u> | | |
| abrasion resistance (DIN EN ISO 12947-2): | approx. 25.000 rubs | |
| pilling resistance (DIN EN ISO 12945-2): | grade 3 | (grades: 1 - 5) (5=excellent/ 1=insufficient) |
| piece lengths: | 60 m and cut service | |
| make up: | rolled | |
| Öko-Tex Standard 100: | A96-0071 (Hohenstein HTTI) | |
| AZO-dyes: | This product complies with the 5th regulation on the change of the consumer product regulations in the FRG, i.e. no dyes made of azoic compounds are employed which might release amines named in the above regulation. | |