





Technical data

article:	<u>drapilux-246</u>	
texture:	atlas weave	
description:	structured dim-out, uni (piece-dyed)	
characteristics:	 flammstop  Dim Out fabric	 drapilux akustik  suitable for bedspreads
repeat (h/w):	---	
material composition:	100 % Polyester (<i>flame-retardant polyester FR</i>)	
height:	approx. 300 cm (↓)	
weight per sqm	approx. 375 g	
colours/designs	23 designs <u>slight deviations in colour possible</u>	
official textile marks:	100 % PES	
fire tests:	meeting international demand of DIN 4102 (B1), M1 Non Feu (B+F+E) , BS 5867 (GB), Classe 1 (I), EN 13773 <u>IMO Res.MSC.307(88)-(2010 FTP Code) in process</u>	
cleaning recommendation:	    	
rest shrinkage at 60°C:	approx. 1-2 %	
light resistance (ISO 105/B02):	grade 5-6	(grades: 1 - 8) (8=excellent/ 1=insufficient)
washing resistance (ISO 105/C01):	grade 3-4	(grades: 1 - 5) (5=excellent/ 1=insufficient)
rubbing test (ISO 105/X12)	dry/wet: grade 4	(grades: 1 - 5) (5=excellent/ 1=insufficient)
<u>Martindale-test (DIN EN 14465):</u>		
abrasion resistance (DIN EN ISO 12947-2):	approx. 10.000 rubs	
pilling resistance (DIN EN ISO 12945-2):	grade 4-5	(grades: 1 - 5) (5=excellent/ 1=insufficient)
piece lengths:	40 m	
make up:	rolled	
Öko-Tex Standard 100:	A96-0071 (Hohenstein HTTI)	
AZO-dyes:	This product complies with the current change of the consumer product regulations in the FRG, i.e. no dyes made of azoic compounds are employed wich might release amines that are named in the above regulation.	