










Technical data

article:	<u>drapilux-764</u>	
texture:	Cross weave	
description:	Filtra-Sol Sheers with weighted tape (inbetween, block stripe)	
characteristics:	 flammstop  suitable as side panel	
	 drapilux bioaktiv	
	 drapilux air	
repeat (h/w):	approx. --- x 116 cm (↔)	
material composition:	100 % Polyester (<i>flame-retardant polyester Trevira CS</i>)	
height:	approx. 320 cm (‡) - (width to order = 321 cm)	
weight per sqm	approx. 80 g	
colours/designs	3 designs <u>slight deviations in colour possible</u>	
official textile marks:	100 % PES	
fire tests:	meeting international demand of DIN 4102 (B1), EN 13773 (class 1), M1 Non Feu (B+F+E) , BS 5867 (GB), Classe 1 (I), IMO Res.MSC.307(88)-(2010 FTP Code)	
cleaning recommendation:	    	
rest shrinkage at 40°C:	approx. 1,0 %	
light resistance (ISO 105/B02):	grade 5-6	(grades: 1 - 8) (8=excellent/ 1=insufficient)
washing resistance (ISO 105/C01):	grade 3-4	(grades: 1 - 5) (5=excellent/ 1=insufficient)
rubbing test (ISO 105/X12)	dry/wet: grade 3-4	(grades: 1 - 5) (5=excellent/ 1=insufficient)
<u>Martindale-test (DIN EN 14465):</u>	----	
abrasion resistance (DIN EN ISO 12947-2):	----	
pilling resistance (DIN EN ISO 12945-2):	(grades: 1 - 5) (5=excellent/ 1=insufficient)	
piece lengths:	40 m and cut service	
make up:	rolled doubled	
Öko-Tex Standard 100:	ACB ; test-No. A96-0071; FI Hohenstein	
AZO-dyes:	This product complies with the 5th regulation on the change of the consumer product regulations in the FRG, i.e. no dyes made of azoic compounds are employed wich might release amines that are named in the above regulation.	