

TECHNICAL INFORMATION



Physical properties

Total weight: 460g/m² (nominal)
Vinyl Weight: 400g/m² (nominal)



Substrate Type: Osnaburg Scrim
Fabric Baker

Substrate weight: 60g/m² (nominal)

Other specifications available

Tensile Strength: MD 80 N/cm (nominal)
TD 60 N/cm (nominal)

Tear Strength: 8500 mN (nominal)



Roll size:

137cm x 27.4m - cut lengths available



Fire Rating:

Class 'O' to the requirements of Approved Document B of the British Building Regulations (Class 1, BS 476 part 7)
Euroclass B - s2, d0. Class A ASTM E-34 Tunnel Test.



Adhesive:

Fabric backed vinyls - Newmor Heavy.
Varies with substrate - please enquire.



Bacteria Resistance:

Contains an active Fungicide.



Light Fast:

Excellent Light Fastness
BS EN ISO 105-B02 6

LRV = Light reflective value

Specifications

Conforms to the requirements of BS EN 15102, BS EN 259 and WA - Quality Standard W-101.

Stain/Chemical Resistance:

Pass ASTM D-1308-1987 Federal Spot Test.
Resistant to temporary staining of oils, fats, mild acids and alkalis.

Quality Assurance:

Our management systems and production procedures comply with ISO 9001 : 2015, the internationally recognised Quality Standard.

Availability:

Every product stocked in depth.
Please allow 5/7 days for delivery.

Origin:

Designed, coloured, manufactured and stocked in the USA

Warranty:

Newmor offers a five year warranty against manufacturing defects.
Full details available on application.

Samples:

Larger samples are readily available on request.

Maintenance:

Fully washable and in most cases products can be scrubbed repeatedly to remove any marks without damaging the product itself. Also able to withstand the use of chlorine releasing agent solutions.



Newmor
WALLCOVERINGS

UK SALES:
T: 01938 551990
E: sales@newmor.com

EXPORT SALES:
T: + 44 (0) 1938 55 2671
E: enquires@newmor.com