



PRIME
Hanging fabrics

 **svensson**



8000



6510



8300




6900



6830




6731




8540



8790



3370




3280




3062




6518




3036



3318



3527



3536




3663



3752



3612



4663

PRIME

Hanging fabrics

Design by: Cathrine Ahlenius

Width: 150 cm

Weight: 360 g/m²

Material: Trevira CS 100%

Shrinkage: 2 %

Color fastness:

Against dry rubbing according to EN ISO 105-X12:

- 4 (Scale 1-5)

Against light according to EN ISO 105-B02

- 5-7 (Scale 1-8)

Against washing according to EN ISO 105-C06

- 5 (Scale 1-5)

Against wet rubbing according to EN ISO 105-X12:

- 3 (Scale 1-5)

Flame retardancy:

- DIN 4102, B1- NF P 92-503-507,

M1- EN 13773, Class 1- SN 198898- BS 5867:

- NF P 92-503-507, M1

- EN 13773, Class 1

- SN 198898- BS 5867: Part 2, Type B

- IMO FTP Code 2010: Part 7

Acoustics:

Measurement of sound absorption in a reverberation room: EN ISO

354:2003. Ration of sound absorption

EN ISO 11654:1997: w = 0,35, Class

D

Care instructions:



Certificates:



For further information:

Svensson
511 82 Kinna, Sweden

T: +46 320 20 92 00

F: +46 320 21 10 10

E: info@ludvigsvensson.com






5262



6223



6236




6033




4823




4324



4435



4572



4364

PRIME

Hanging fabrics

Design by: Cathrine Ahlenius
Width: 150 cm
Weight: 360 g/m²
Material: Trevira CS 100%
Shrinkage: 2 %

Color fastness:
Against dry rubbing according to EN ISO 105-X12:
 - 4 (Scale 1-5)
Against light according to EN ISO 105-B02
 - 5-7 (Scale 1-8)
Against washing according to EN ISO 105-C06
 - 5 (Scale 1-5)
Against wet rubbing according to EN ISO 105-X12:
 - 3 (Scale 1-5)

Flame retardancy:
 - DIN 4102, B1- NF P 92-503-507, M1- EN 13773, Class 1- SN 198898- BS 5867:
 5867:
 - NF P 92-503-507, M1
 - EN 13773, Class 1
 - SN 198898- BS 5867: Part 2, Type B
 - IMO FTP Code 2010: Part 7

Acoustics:
 Measurement of sound absorption in a reverberation room: EN ISO 354:2003. Ration of sound absorption EN ISO 11654:1997: w = 0,35, Class D

Care instructions:



Certificates:



For further information:

Svensson
 511 82 Kinna, Sweden

T: +46 320 20 92 00
 F: +46 320 21 10 10
 E: info@ludvigsvensson.com

